

DENSO PASTE

Petrolatum Tape Primer

Description

Denso Paste is a soft brown petrolatum primer containing moisture displacing corrosion inhibiting compounds for application by stiff brush or gloved hand at normal ambient temperature. It does not dry, harden or crack.

Uses

Primarily used as a primer prior to the application of Denso petrolatum tapes. Denso Paste will penetrate existing rust, displace moisture, pacify the surface and aid the adhesion of petrolatum tapes and mastics. It is also used as a temporary coating for exposed metal.

Features

- Minimal surface preparation (SSPC SP 2-3)
- Can be applied in any climate
- Can be applied to wet surfaces
- Contains no V.O.C.'s
- Can be applied by inexperienced personnel
- No shut downs necessary
- Meets AWWA C-217

Application

Prepare surfaces by removing all loose scale, rust or other foreign matter in accordance to SSPC SP2 "Hand Tool Cleaning" or SP3 "Power Tool Cleaning". High pressure water wash of 3,000 - 7,000 psi (20.68 - 48.48 MPa) is also suitable. Apply a thin uniform coat of Denso Paste to entire surface with gloved hand, brush or rag.



Denso Paste

PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH	METRIC
Solids Content	>98%	>98%
Specific Gravity	1.08	1.08
Specific Volume	26 cu in/lb.	925 cc/kg
Flash Point	>356°F	>180°C
Maximum Service Temperature	158°F	70°C
Coverage (Per Pail)	22 ft ² /lb.	4.5 m ² /kg
Packaging	4 ea 5.5 lb tubs	4 ea 2.5 kg tubs

COVERAGE PER CASE:

484 ft² per case

(45.06 m² per case)

PACKAGING:

4 each 5.5 lb tubs per case

(4 each 2.5 kg tubs per case)

Also available in 55 lb (25 kg) drums

Product Distributed By:

corrpro®

Toll Free Number – **1-800-661-8390**



DENSO NORTH AMERICA

HOUSTON:

9747 Whithorn Drive,
Houston, Texas,
U.S.A. 77095
Tel: 281-821-3355
Fax: 281-821-0304

TORONTO:

90 Ironside Crescent,
Unit 12, Toronto,
Ontario, Canada M1X1M3
Tel: 416-291-3435
Fax: 416-291-0898

www.densona.com

A Member of Winn & Coales International

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.